CORIAN® SOLID SURFACE PERFORMANCE PROPERTIES

PHYSICAL PROPERTIES

PROPERTY	TEST	TYPICAL RESULT
Density	ISO 1183	1.75 g/cm3
Approximate weight per square meter 6 mm		10.5 kg
Approximate weight per square meter 12 mm ¹		21 kg
Thermal expansion	ASTM D 696	3,9 x 10 ⁻⁵ mm/mm °C
Hardness - Rockwell "M" scale	EN ISO 19712-2 (ISO 2039-2)	>85
Hardness - Barcol impressor	EN ISO 19712-2 (ASTM D 2583)	56
Hardness - Ball indentation	EN ISO 19712-2 (ISO 2039-1)	290 N/mm²
Surface hardness (Mohs index)	DIN EN 101	2-3

MECHANICAL PROPERTIES

PROPERTY	TEST	TYPICAL RESULT
Flexural modulus	ISO 178	8800 MPa
Flexural strength		71 MPa
Tensile strength	ISO 527-2	47 MPa
Tensile elongation at break		0.8%
Compressive strength	ISO 604	119 MPa

Typical results for 12mm solid colours unless gauge is specified. Properties may vary by aesthetic. These values are not intended for engineering calculations, if precise calculations are required contact DuPont for additional information.

¹ For information on specific colours, please see Corian* Solid Surface The Complete Colour Palette. For information on Fire Performance please see Corian* Solid Surface Fire Performance (K-28300-EMEA).

FITNESS FOR USE

PROPERTY	TEST	TYPICAL RESULT
Light resistance (Xenon Arc)	EN ISO 19712-2	Pass
Weatherability ¹	ASTM G 155	ΔE* ₉₄ <5 in 1,000 hrs.
Resistance to impact by large diameter ball	EN ISO 19712-2	no breaks
Stain/chemical-resistance test		Pass
Resistance to cigarette burns		Pass
Resistance to dry heat		Pass
Resistance to wet heat		Pass
Hot/cold cycle water-resistance test		Pass
Load test		Pass
Dimensional stability	ISO 4586-2	Pass
Resistance to surface wear		0.18% wt/25 revolutions
Fungi and bacteria resistance	ISO 846	Does not support microbial growth
Resistance to boiling water - surface change	DIN ISO 4586 T7	No visible change

Typical results for 12mm solid colours unless gauge is specified. Properties may vary by aesthetic. These values are not intended for engineering calculations, if precise calculations are required contact DuPont for additional information.

PLEASE VISIT OUR WEB SITE: WWW.CORIAN.UK OR CONTACT YOUR CORIAN® REPRESENTATIVE FOR MORE INFORMATION ABOUT CORIAN® SOLID SURFACE.

This information is based on technical data that DuPont de Nemours Inc. and its affiliates ("DuPont") believe to be reliable, and is intended for use by persons having technical skill and at their own discretion and risk. DuPont cannot and does not warrant that this information is absolutely current or accurate, although every effort is made to ensure that it is kept as current and accurate as possible. Because conditions of use are outside DuPont's control, DuPont makes no representations or warranties, express or implied, with respect to the information, or any part thereof, including any warranties of title, non-infringement of copyright or patent rights of others, merchantability, or fitness or suitability for any purpose and assumes no liability or responsibility for the accuracy, completeness, or usefulness of any information. This information should not be relied upon to create specifications, designs, or installation guidelines. The persons responsible for the use and handling of the product are responsible for ensuring the design, fabrication, or installation methods and process present no health or safety hazards. Do not attempt to perform specification, design, fabrication, or installation work without proper training or without the proper personal protection equipment. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents. DuPont shall have no liability for the use of or results obtained from such information, whether or not based on DuPont's negligence. DuPont shall not be liable for (i) any damages, including claims relating to the specification, design, fabrication, installation, or combination of this product with any other product(s), and (ii) special, direct, indirect or consequential damages. DuPont reserves the right to make changes to this information and to this disclaimer. DuPont encourages you to review this information and this disclaimer periodically for any updates or changes. Your continued access or use of this information shall be d

Corian* and the Corian* logo system are registered trademarks or trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2024 DuPont. All rights reserved.

K-26829-EMEA 02/24

¹ For information on specific colours, please see Corian* Solid Surface The Complete Colour Palette. For information on Fire Performance please see Corian* Solid Surface Fire Performance (K-28300-EMEA).